

Tub & Tile Siliconized Acrylic Latex Sealant

Product Specifications



MAINLINE TUB & TILE is a quality siliconized acrylic latex sealant. It can be used on a wide variety of interior and exterior surfaces, delivering good adhesion and durability. **TUB & TILE** caulk forms a flexible, durable, airtight, water resistant seal that offers protection from environmental conditions and features an easy to clean bead. Once cured, **MAINLINE TUB & TILE** sealant is mildew resistant and meets ASTM C-834, Type OP, Grade 0°C. **TUB & TILE** caulk is designed to be used where an acrylic adhesive sealant is ideal for sealing or setting the following: Sinks, Showers, Counter Tops, and similar applications. **MAINLINE TUB & TILE** sealant is easily cleaned with soap and water.

- Multi-Purpose Tub & Tile Sealant
- Cured caulk resists mold and mildew
- Paintable
- Low odor
- Long lasting Flexibility
- 40 Year Durability Guarantee
- Soap and water clean up



Packaging	Color	Part#	UPC#
10.1 fl oz. (299 mL)	White	ML10213	722301392737
5.5 fl oz. (162 mL)	White	ML11714	722301392720
5.5 fl oz. (162 mL)	Clear	ML11713	722301392713
5.5 fl oz. (162 mL)	Almond	ML11715	722301392669
5.5 fl oz. (162 mL)	Biscuit	ML11716	722301392676

SUGGESTED USES:

- Sinks
- Showers
- Tubs
- Tile
- Penetrations
- Trim around window and doors
- Countertops
- Fixtures
- Plumbing
- Vents

PERFORMANCE CHARACTERISTICS:

- ASTM C-834 Type OP, Grade 0°C
- Up ½" in properly designed joints
- Paintable
- 40 year durability guarantee

Warranty: See warranty information for more details.

All dimensions listed are nominal. MAINLINE® reserves the right to make product and material changes at any time without notice.



Contact your sales representative for more information or visit our website at mainlinecollection.com

Tub & Tile Siliconized Acrylic Latex Sealant

Product Specifications



SURFACE PREPARATION:

- Surface must be dry and free of dirt, dust, oil, mildew, loose paint, old caulk or other contaminants.
- Areas with existing mold or mildew should first be cleaned with a mild bleach solution.
- Only apply when sealant surface and air temperature are above 40°F and rising.
- Do not apply on surfaces above 120° F or when rain is expected

APPLICATION:

- Cut nozzle at a 45° angle.
- Properly designed joint not to exceed 1/2" in width.
- Use backer rod for joints deeper than 1/2".
- Tool or smooth bead within 10 to 15 minutes, depending on climatic conditions. Tooling immediately ensures best adhesion and a smooth finished surface.
- NOTE: Clear Tub & Tile will dispense white and dry clear. Full clarity may take from 7 to 14 days.
- Sealant maybe removed and tools cleaned prior to curing with soap and water.
- Allow 24 hours curing time before applying paint and using bath or shower
- Depending on the environmental conditions, full cure should occur in 7-14 days.

PHYSICAL & CHEMICAL CHARACTERISTICS:

Vehicle:	Acrylic Polymer / Siliconized
VOC:	Non-chemically curing sealant. VOC (less exempt solvents) is <1.5%
Pigment:	Calcium Carbonate
Solids:	Approximately 72.5%
Weight per Gallon:	11.00 ± 0.5
Service Temperature:	0°F to 160°F
Temperature Application Range:	40°F and rising. Air temp no hotter than 95° and substrate not hotter than 120°F
Freeze Thaw Stability:	Passes 5 Cycles@ 0°F (1 cycle = 16hrs. @ 0°F, 8hrs at 75°F)
Flash Point:	None
Applications:	Interior / Exterior
Life Expectancy:	40 year performance
Shelf Life:	24 months when stored at 50°F to 80°F
Coverage - 10.1 fl oz:	54 linear ft. at a 3/16" bead
Odor:	Mild Sweet Acrylic
Tooling Time:	10 to 15 Minutes
Tack Free Time:	60 Minutes
Cure Time:	24 hours before painting
Curing Time Before Use:	24 hours before exposing to water in tub or shower

Warranty: See warranty information for more details.

All dimensions listed are nominal. MAINLINE® reserves the right to make product and material changes at any time without notice.



Contact your sales representative for more information or visit our website at mainlinecollection.com

Tub & Tile Siliconized Acrylic Latex Sealant

Product Specifications



CLEANUP

Immediately after use, clean equipment with soap and water. Remove cured sealant by cutting with a sharp-edged tool. Remove thin films by abrading.

SAFETY

See Safety Data Sheet (SDS) for safety information or product label. During cure acetic acid is released and vapors should not be inhaled. Good ventilation is required. Should uncured silicone rubber come into contact with eyes or mucous membranes, the affected area must be rinsed thoroughly with water. To request a Safety Data Sheet visit the manufacturer's web site at www.towersealants.com or contact Tower Sealants at 866-897-7568. For medical emergencies only, call ChemTrec 1-800-424-9300.

MORE INFORMATION

Manufactured by: Tower Sealants, 2095 Memorial Park Rd., Gainesville, GA 30504 U.S.A

Customer Service: (866) 897-7568

Website: www.towersealants.com

Technical Questions: tech@towersealants.com

Warranty: See warranty information for more details.

All dimensions listed are nominal. MAINLINE® reserves the right to make product and material changes at any time without notice.



Contact your sales representative for more information or visit our website at mainlinecollection.com